A	
PTO	
S. 972	
269/	
38	

PTO/SB/05 (08-00)

Please type a plus sign (+) inside this box ——

Approved for use through 10/31/2002, OMB 0651-0032 U.S. Patent and Trademark Office; U.S. DEPARTMENT OF COMMERCE

Joel E. Goldstein

06076 USA

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number.

Attorney Docket No.

First Inventor

UTILITY PATENT APPLICATION TRANSMITTAL

	Title Reduced Formaldenyde Nonwoven Binders vynich					
(Only for new nonprovisional applications under 37 CFR 1.53(b))	Express Mail Label No. EL685717250US					
APPLICATION ELEMENTS See MPEP chapter 600 concerning utility patent application contents.	ASSISTANT Commissioner for Patents ADDRESS TO: Box Patent Application Washington, DC 20231					
Fee Transmittal Form (e.g., PTO/SB/17) (Submit an original and a duplicate for fee processing) Applicant claims small entity status. See 37 CFR 1.27. Specification [Total Pages 12] (preferred arrangement set forth below) - Descriptive title of the invention - Cross Reference to Related Applications - Statement Regarding Fed sponsored R & D - Reference to sequence listing, a table, or a computer program listing appendix - Background of the Invention - Brief Summary of the Invention - Brief Description of the Drawings (if filed) - Detailed Description - Claim(s) - Abstract of the Disclosure	7. CD-ROM or CD-R in duplicate, large table or Computer Program (Appendix) 8. Nucleotide and/or Amino Acid Sequence Submission (if applicable, all necessary) a. Computer Readable Form (CRF) b. Specification Sequence Listing on: i. CD-ROM or CD-R (2 copies); or ii. D paper c. Statements verifying identity of above copies ACCOMPANYING APPLICATION PARTS 9. Assignment Papers (cover sheet & document(s)) 10. 37 CFR 3.73(b) Statement Power of (when there is an assignee)					
4. Drawing(s) (35 U.S.C. 113) [Total Sheets] 5. Oath or Declaration [Total Pages] a. Newly executed (original or copy) Copy from a prior application (37 CFR 1.63 (d)) b. (for continuationIdivisional with Box 17 completed) i. DELETION OF INVENTOR(S) Signed statement attached deteting inventor(s) named in the prior application, see 37 CFR 1.63(d)(2) and 1.33(b). 6. Application Data Sheet. See 37 CFR 1.76 17. If a CONTINUING APPLICATION, check appropriate box, and sup or in an Application Data Sheet under 37 CFR 1.76:						
Continuation Divisional Continuation-in-part (CIP) Prior application information: Examiner For CONTINUATION OR DIVISIONAL APPS only: The entire disclosure of the Box 5b, is considered a part of the disclosure of the accompanying continu	Group / Art Unit: prior application, from which an oath or declaration is supplied under lation or divisional application and is hereby incorporated by reference.					
The incorporation can only be relied upon when a portion has been inadvented as the concept of the incorporation can only be relied upon when a portion has been inadvented as the incorporation can only be relied upon when a portion has been inadvented as the incorporation can only be relied upon when a portion has been inadvented as the incorporation can only be relied upon when a portion has been inadvented as the incorporation can only be relied upon when a portion has been inadvented as the incorporation can only be relied upon when a portion has been inadvented as the incorporation can only be relied upon when a portion has been inadvented as the i						
Customer Number or Bar Code Label	or Correspondence address below					
Name 23543	II III III					
Address Air Products and Cher	nicals, Inc.					
City	State Zip Code					
Country Te	lephone Fax					
Name (Print/Type) Russell L. Brewer	Registration No. (Attorney/Agent) 25,073					
Signature Lusse I Duna	Date 10/30/2000					

Burden Hour Statement: This form is estimated to take 0.2 hours to complete. Time will vary depending upon the needs of the individual case. Any comments on the amount of time you are required to complete this form should be sent to the Chief Information Officer, U.S. Patent and Trademark Office, Washington, DC 20231. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Assistant Commissioner for Patents, Box Patent Application, Washington, DC 20231.

PTO/SB/17 (09-00)
Approved for use through 10/31/2002. OMB 0651-0032
U.S. Patent and Trademark Office; U.S. DEPARTMENT OF COMMERCE
Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number.

FEE TRANSMITTAL for FY 2001

Patent fees are subject to annual revision.

TOTAL AMOUNT OF PAYMENT

Complete if Known						
Application Number						
Filing Date						
First Named Inventor	Joel E. Goldstein					
Examiner Name						
Group Art Unit						
Attorney Docket No.		06076 USA				

METHOD OF PAYMENT FEE CALCULATION (continued)					
1. X The Commissioner is hereby authorized to charge indicated fees and credit any overpayments to:	3. ADDITIONAL FEES				
indicated fees and credit any overpayments to: Deposit	Large Entity Small Entity Fee Fee Fee Fee Fee Fee Description	E B			
Account Number 01-0493	Code (\$) Code (\$)	Fee Paid			
Denosit	105 130 205 65 Surcharge - late filing fee or oath				
Account Name Air Products and Chemicals, Inc	127 50 227 25 Surcharge - late provisional filing fee or cover sheet				
X Charge Any Additional Fee Required Under 37 CFR 1.16 and 1.17	139 130 139 130 Non-English specification				
Applicant claims small entity status.	147 2,520 147 2,520 For filing a request for ex parte reexamination				
See 37 CFR 1.27 2. Payment Enclosed:	112 920* 112 920* Requesting publication of SIR prior to Examiner action				
2. Payment Enclosed: Check Credit card Money Order Other	113 1,840* 113 1,840* Requesting publication of SIR after Examiner action				
FEE CALCULATION	115 110 215 55 Extension for reply within first month				
1. BASIC FILING FEE	116 390 216 195 Extension for reply within second month				
Large Entity Small Entity	117 890 217 445 Extension for reply within third month				
Fee Fee Fee Fee Description	118 1,390 218 695 Extension for reply within fourth month				
404 740 004 005	128 1,890 228 945 Extension for reply within fifth month				
101 710 201 355 Utility filing fee 710	119 310 219 155 Notice of Appeal				
107 490 207 245 Plant filing fee	120 310 220 155 Filing a brief in support of an appeal				
108 710 208 355 Reissue filing fee	121 270 221 135 Request for oral hearing				
114 150 214 75 Provisional filing fee	138 1,510 138 1,510 Petition to institute a public use proceeding				
	140 110 240 55 Petition to revive - unavoidable				
SUBTOTAL (1) (\$) 710	141 1,240 241 620 Petition to revive - unintentional				
2. EXTRA CLAIM FEES	142 1,240 242 620 Utility issue fee (or reissue)				
Fee from Extra Claims below Fee Paid	143 440 243 220 Design issue fee				
Total Claims $7 - 20^{++} = 0 \times 18 = 0$	144 600 244 300 Plant issue fee				
Independent	122 130 122 130 Petitions to the Commissioner				
Multiple Dependent =	123 50 123 50 Petitions related to provisional applications]			
	126 240 126 240 Submission of Information Disclosure Strnt				
Large Entity Small Entity Fee Fee Fee Fee Fee Description Code (\$) Code (\$)	581 40 581 40 Recording each patent assignment per property (times number of properties)				
103 18 203 9 Claims in excess of 20	146 710 246 355 Filing a submission after final rejection (37 CFR § 1.129(a))				
102 80 202 40 Independent claims in excess of 3	149 710 249 355 For each additional invention to be				
104 270 204 135 Multiple dependent claim, if not paid	examined (37 CFR § 1.129(b))				
109 80 209 40 ** Reissue independent claims over original patent	179 710 279 355 Request for Continued Examination (RCE)				
110 18 210 9 ** Reissue claims in excess of 20 and over original patent	169 900 169 900 Request for expedited examination of a dasign application				
SUBTOTAL (2) (\$) 0	Other fee (specify)				
**or number previously paid, if greater; For Reissues, see above	*Reduced by Basic Filing Fee Paid SUBTOTAL (3)	0			

or number providue	ny para, ir grouter, r or reassues, see above				
SUBMITTED BY				Complete (i	f applicable)
Name (Print/Type)	Russell L. Brewer	Registration No. (Attorney/Agent)	25,073	Telephone	610-481-7289
Signature	George 20 Sieva			Dat e	10/30/2000

WARNING: Information on this form may become public. Credit card information should not be included on this form. Provide credit card information and authorization on PTO-2038.

Burden Hour Statement: This form is estimated to take 0.2 hours to complete. Time will vary depending upon the needs of the individual case. Any comments on the amount of time you are required to complete this form should be sent to the Chief Information Officer, U.S. Patent and Trademark Office, Washington, DC 20231. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS SEND TO: Assistant Commissioner for Patents, Washington, DC 20231.

10

15

20

TITLE OF THE INVENTION:

REDUCED FORMALDEHYDE NONWOVEN BINDERS WHICH CONTAIN POLYMERIZED UNITS OF N-METHYLOLACRYLAMIDE

BACKGROUND OF THE INVENTION

Nonwoven webs which are comprised of loosely assembled webs or masses of fibers bound together with an adhesive binder have many applications. These include paper towels, disposable diapers, filtration products, disposable wipes, and the like. Vinyl acetate based emulsions incorporating crosslinkable functionality are widely used in the preparation of these nonwoven products. One of the favorite crosslinking systems is based upon N-methylolacrylamide.

The emission of formaldehyde represents a worker safety and health issue, as well as a consumer issue, and there have been significant attempts to prepare adhesive binders having either reduced formaldehyde content or they are formaldehyde-free. Reduction of formaldehyde in vinyl acetate based emulsions has been achieved by using less favored reducing agents to the formaldehyde sulfoxylates, or by reducing the level of N-methylol acrylamide employed in the adhesive binder. Formaldehyde-free binders eliminate both the N-methylol acrylamide and the use of any formaldehyde emitting reducing agent. However, either method for producing vinyl acetate based emulsion polymers for nonwoven webs has been done so at the expense of performance and cost.

Representative patents disclosing adhesive binders having a post-curable comonomer such as N-methylolacrylamide are as follows:

U.S. 3,081,197 discloses a nonwoven binder incorporating an internal plasticizer and a post-curable comonomer such as N-methylolacrylamide.

10

15

20

25

U.S. 3,380,851 discloses a binder comprising an interpolymer of vinyl acetate/ethylene/N-methylolacrylamide for the preparation of nonwoven goods.

U.S. 4,449,978 discloses vinyl acetate/ethylene/N-methylolacrylamide/acrylamide systems for producing nonwoven webs. The advantage of using the N-methylolacrylamide/acrylamide blend has been the ability to reduce the amount of formaldehyde present in the emulsion and in the cured web without a substantial loss of performance.

U.S. 5,540,987 discloses vinyl acetate/ethylene/ N-methylolacrylamide polymers for use in producing nonwoven webs having reduced formaldehyde content as well as reduced formaldehyde content in the cured web. Reduced formaldehyde content is achieved by using a redox system based upon a hydrophobic hydroperoxide and ascorbic acid. These systems result in formaldehyde contents significantly lower than those systems produced using a corresponding reducing agent incorporating no formaldehyde such as sodium metabisulfite or formaldehyde emitting reducing agents such as sodium formaldehyde sulfoxylate.

Several of the approaches to reduced formaldehyde content in nonwoven webs have been directed to actually prepare formaldehyde free nonwoven binders. The approaches pursued for the former include the use of crosslinkers based upon acrylamidobutyraldehyde dialkyl acetal, the methacrylamide derivative, the cyclized version, methyl acrylamidoglycolate methyl ether, allyl glycidyl ether, 3-chloro-2-hydroxypropyl (meth)acrylate and acrylamidoglycolic acid. The problems with these kinds of crosslinkers for nonwoven binders included poorer performance (lower tensile development), activation of the crosslinking chemistry at a pH which is corrosive to the commercial machinery, the requirement to use a more expensive and commercially unavailable novel self-crosslinking monomer and the instability of the self-crosslinking monomer.

10

15

20

BRIEF SUMMARY OF THE INVENTION

The invention relates to improved vinyl acetate based emulsion polymers incorporating N-methylolacrylamide as a crosslinking component for construction of nonwoven webs. The emulsions polymers are prepared by emulsion polymerization of vinyl acetate, N-methylolacrylamide and optional monomers in the presence of a stabilizing system and a redox catalyst system comprised of an oxidizing agent and a reducing agent. The improvement for achieving reduced formaldehyde in the emulsion polymer resides in the use of a glycolic acid adduct of sodium sulfite (a proprietary reducing agent sold under the trademark Bruggolite FF-6) as the reducing agent. Lower formaldehyde levels are achieved in contrast to other formaldehyde free reducing agents such as sodium erythorbate and sodium ascorbate, and to sodium formaldehyde sulfoxylate, or any of the other reducing agents typically used in the preparation of a nonwoven binder employing N-methylolacrylamide as the self-crosslinking monomer.

There are significant advantages associated with the use of the glycolic acid adduct of sodium sulfite in producing vinyl acetate based emulsion binders containing N-methylolacrylamide. They include:

an ability to generate vinyl acetate-based emulsions which are highly suited for use in preparing nonwoven products having substantially reduced formaldehyde levels in the emulsion or latex; and.

an ability to generate nonwoven products having excellent resistance to solvents and water while at the same time having excellent adhesion to the fibers for providing enhanced tensile strength.

25

10

15

20

25

The N-methylolacrylamide containing emulsions for use in producing the nonwoven webs are based on copolymers of vinyl acetate and N-methylolacrylamide. Typically, these are vinyl acetate/ethylene/ N-methylolacrylamide containing polymers, although optionally other monomers may be included in the polymer system as desired. The ethylene content will range broadly from about 10 to 40% and preferably 15 to 30% by weight, yielding an adhesive having a Tg of from -15 to 10°C. Other monomers which may be included in the adhesive binder include vinyl esters of aliphatic carboxylic acids as well as C₁-C₈ alkyl acrylates and methyacrylates. Examples include methylacrylate, methyl methacrylate, ethyl acrylate, butyl acrylate, and 2-ethylhexylacrylate. Small amounts of polyolefinically–unsaturated monomers, e.g., dioctyl and dibutyl maleate, and the like may also be used.

Commercially, N-methylolacrylamide used in the preparation of vinyl acetate-based nonwoven binders is obtained with about a 48% aqueous solution with up to about 2% acrylamide. Another type of N-methylolacrylamide product which may be used herein is an N-methylolacrylamide/acrylamide mixture. Often this blend is present in a 1:1 molar ratio. Isobutoxy methyl acrylamide is an optional crosslinker but is not preferred to N-methylolacrylamide.

Monomers other than vinyl acetate and ethylene are polymerized in amounts of less than 10% by weight and generally even less than 5% by weight. These levels are exclusive of the level of N-methylolacrylamide or of the level of N-methylolacrylamide blend used in preparing the emulsion polymer. The crosslinking monomer N-methylolacrylamide is generally incorporated at levels of from 0.5 to 10% by weight, although typically levels are from about 1.5 to 5% by weight of the polymer.

Stabilizing systems used for preparing the vinyl acetate based polymers include nonionic emulsifiers such as polyoxyethylene condensates of the formula $R-(CH_2CH_2O)_n-H$ wherein R is the residue of fatty alcohol containing 10 to 18 carbon

10

15

20

25

atoms, an alkyl phenol, a fatty acid containing 10 to 18 carbon atoms, an amide or amine, and the like. Examples of polyethoxylated condensates are based on ethoxylated tridecyl alcohol, fatty alcohols, i.e., lauryl alcohol, octyl phenol, nonyl phenol or a secondary alcohol. Furthermore, the stabilizing package may include sodium vinyl sulfonate, sodium dodecyl benzene sulfonate, dioctyl sulfosuccinate, disodium lauryl sulfosuccinate, sodium lauryl sulfate, sodium methyl 2-sulfolaurate and the sodium or ammonium salts of the sulfonates or phosphates of any of the above described nonionic surfactants. Often combinations of emulsifying agents are used; e.g., a relatively hydrophobic emulsifying agent used in combination with the relatively hydrophilic agent.

The amount of active surfactants in the stabilizing system based upon total monomers typically ranges from 1.5% to 6.0%, preferably from 2.5% - 4.0% by weight. The ratio between the individual components in the surfactant stabilizing package is one of design.

One of the keys to producing the emulsion polymers having reduced free formaldehyde in the latex as well as in the dried cured web is in the initiator system used to effect polymerization of the monomers. The initiator system employed herein is a redox system based upon an oxidizing agent and a particular class of reducing agents. A wide variety of oxidizing agents may be used. Preferably, these oxidizing agents are inorganic and hydrophobic peroxides, such as hydrogen peroxide, *t*-butylhydroperoxide and benzoyl peroxide. Thermal initiators such as the persulfates, e.g., ammonium and potassium persulfate, may be used.

Although nonformaldehyde-containing reducing agents, e.g., sodium metabisulfite and ascorbic acid or alkali metal salt thereof have been used in the past in combination with an oxidizing agent, it has been found that a class of sulfinic acid derivatives and particularly the glycolic acid adduct of sodium sulfite affords an

exceptional reduction in free formaldehyde content in the emulsions as compared to the other nonformaldehyde emitting reducing agents.

The sulfinic acid derivatives are represented by the formula:

$$\begin{array}{c|c}
O & R_1 \\
S & R_2 \\
R_3 & R_3
\end{array}$$

5

where M is a hydrogen atom an ammonium atom or a monovalent metal ion, e.g., sodium, potassium or an equivalent of a divalent metal, e.g., zinc; R_1 is OH or NR_4R_5 wherein R₄ and R₅ each are H or C₁-C₆ alkyl; R₂ is H or an alkyl, alkenyl, cycloalkyl or aryl and the like, and R₃ is CO₂M. The preferred reducing agent is formed by reacting sodium dithionite with glycolic acid. Other examples of sulfinic acid compounds include 4-methoxyphenyl 2-hydroxyphenyl hydroxymethyl sulfinic acid-sodium salt: hydroxymethyl sulfinic acid-sodium salt; 2-hydroxy-2-sulfinato acetic acid-disodium salt; 2-hydroxy-2-sulfinato acetic acid-zinc salt; 2-hydroxy-2-sulfinato propionatic acid-disodium salt; ethyl 2-hydroxy-2-sulfinato propionate-sodium salt, and the like.

15

10

This class of reducing agents is the only one that seems to offer these significant reductions in vinyl acetate-based adhesives for use in preparing nonwoven products utilizing N-methylolacrylamide as the crosslinking monomer. Preferred results are obtained with the glycolic acid adduct of sodium sulfite which is sold under the trademark Bruggolite FF-6.

20

The initiator system comprised of an oxidizing and reducing agent is employed in an amount of from about 0.1 to 2% by weight of the total monomers utilized in the polymerization process. The molar ratio of oxidizing agent to reducing agent typically is greater than 1. Conventionally the molar amount of the reducing agent used is less than the molar amount of the oxidizing agent.

10

15

Temperatures for effecting polymerization range from about 25 to 85°C with typical polymerizations being operated in the range of from 55 to 70°C. Reactor pressures range from about 300 to 1200 psig and are dependent upon the level of ethylene that is desired to be incorporated into the polymer.

The manufacture of nonwoven webs is well known, and exemplary processes are noted in U.S. 4,449,978 which is incorporated by reference. Conventionally a mass of fibers are deposited or arranged on a web by an air-laid, etc., technique and then contacted with an aqueous polymeric binder in amounts sufficient to provide about 10 to 100%, by weight of the emulsion polymer, on a dry basis, based on the weight of the starting web. The water is removed and the polymer crosslinked through its self-crosslinking mechanism by use of an acid catalyst. Drying temperatures typically range from 150 to 200°F for about 4 to 6 minutes followed by a cure of 300 to 310°F for 3 to 5 minutes.

A wide variety of fibrous materials may be used for preparing nonwoven webs, including cellulosic fibers, polyester, polyolefin, polyurethane, etc. Cellulose is one of the more common fibrous materials which is used for producing paper nonwovens such as disposable diapers, consumer towels, disposable wipes, and filtration products.

The following examples are provided to illustrate various embodiments of the invention and are not intended to restrict the scope thereof.

20

25

Example 1

Polymerization of Vinyl Acetate/Ethylene/N-methylolacrylamide Binder
Using Glycolic Acid Adduct of Sodium Sulfate Reducing Agent

The polymerization of various vinyl acetate-ethylene/N-methylolacrylamide systems was carried out in a one gallon stirred, stainless steel reaction vessel equipped with a jacket. The reaction vessel was charged initially with 800.0 g of deionized water,

10

15

305.0 g of sodium octylphenol ethoxylate sulfate, 3EO (sold under the trademark Polystep C-OP3S), 0.91 g of sodium citrate, 2.4 g of 50% aqueous citric acid, 2.3 g of 5% aqueous ferric ammonium sulfate and 1558.0 g of vinyl acetate. While stirring, 240.0 g of ethylene was introduced below the surface of the liquid in the reaction vessel in order that the interpolymers would have a vinyl acetate:ethylene weight ratio of about 80:20. The reaction vessel was heated to 50 °C.

The following three aqueous solutions were intermittently added to the reaction vessel over the course of the reaction (on a delay basis); (a) 7.5% Bruggolite FF-6, (b) 3.0 % *t*-butylhydroperoxide and (c) 291.6 g of a 48% aqueous solution of functional monomers (a commercially available material comprised of approximately 28% aqueous NMA and 20% aqueous acrylamide). After four hours the N-methylolacrylamide/acrylamide (MAMD) delay was complete and the other two delays continued for another 30 minutes. The reaction was terminated by cooling.

The resulting dispersion contained 51.5% solids, a pH of 5.3, and a Brookfield viscosity of 182 cps at 60 rpm and a #3 spindle. The glass transition temperature, T_g , of the polymer was 8.9 °C. The grit level of the dispersion was 156 ppm on a 100 mesh screen and 25 ppm on a 325 mesh screen.

Example 2

20 Comparison of Vinyl Acetate/Ethylene/N-methylolacrylamide Binders

Using Glyolic Acid Adduct of Sodium Sulfate Reducing Agent and Ascorbic Acid

Three comparative vinyl acetate/ethylene/self-crosslinking monomer dispersions were prepared where the only significant differences to the Example 1 formulation was in

10

15

20

the amount of the reducing agent used in the redox couple and in the amount of ethylene in the resultant polymer.

The first vinyl acetate/ethylene/N-methylolacrylamide emulsions polymers were low T_g dispersions, -14 °C. The dispersion formed with the Bruggolite FF-6 based system gave a formaldehyde level of 3.3 ppm while the sodium erythorbate based system gave a formaldehyde level of 27.2 ppm.

The second vinyl acetate/ethylene/N-methylolacrylamide emulsion polymers were high $T_{\rm g}$ dispersions, 10 °C. The Bruggolite FF-6 based systems gave a formaldehyde level of 8.6 ppm while the sodium erythorbate based systems gave a formaldehyde level of 57.1 ppm.

The third second vinyl acetate/ethylene/N-methylolacrylamide emulsion polymers were medium T_g dispersions, 0 °C, but the level of self-crosslinking monomer was 50% higher than either of the other two examples. The Bruggolite FF-6 based system gave a formaldehyde level of 6.8 ppm while the sodium erythorbate based system gave a formaldehyde level of 47.5 ppm.

In summary, these data show that not only does the Bruggolite FF6 reducing agent based the presumed glycolic acid adduct of sodium sulfite provide excellent results in terms of polymerization rates but is also more effective in reducing the free formaldehyde in the emulsion than other formaldehyde free reducing agent, ascorbic acid. Lower free formaldehyde content in the emulsion may also result in al lower level of free formaldehyde level in the final dried and cured nonwoven web. Further, the tensile properties and absorbencies of the webs produced using the Bruggolite FF-6 reducing agent are indistinguishable one using the ascorbic acid as the reducing agent, all other parameters remaining the same.

25

CLAIMS

What is claimed is:

1. In a vinyl acetate based polymer based emulsion formed by the polymerization of vinyl acetate and N-methylolacrylamide, optionally other monomers, in the presence of a stabilizing system and a redox catalyst system comprised of an oxidizing agent and a reducing agent, the improvement for reducing formaldehyde emissions in the emulsion, which comprises:

forming said vinyl acetate based polymer emulsion utilizing as the reducing component of the redox catalyst system a reducing agent of the formula:

10

5

$$\begin{array}{c|c}
O & R_1 \\
S & R_2 \\
R_3 & R_3
\end{array}$$

where M is a hydrogen atom, an ammonium atom or a monovalent metal ion, R_1 is OH or NR_4R_5 wherein R_4 and R_5 each are H or C_1 - C_6 alkyl; R_2 is H or an alkyl, alkenyl, cycloalkyl or aryl and the like, and R_3 is CO_2M .

15

2. The vinyl acetate polymer based emulsion of Claim 1 in which the vinyl acetate polymer-based emulsion comprises ethylene in an amount of from about 10 to 40% by weight of the polymer.

20

3. The vinyl acetate polymer based emulsion of Claim 2 wherein the N-methylolacrylamide is present in an amount of from about 0.5 to 10% by weight of the polymer.

10

- 4. The vinyl acetate polymer based emulsion of Claim 3 wherein the reducing agent represented by the formula is selected from the group consisting of: 2-hydroxyphenyl hydroxymethyl sulfinic acid-sodium salt; 4-methoxyphenyl hydroxymethyl sulfinic acid-sodium salt; 2-hydroxy-2-sulfinato acetic acid-disodium salt; 2-hydroxy-2-sulfinato acetic acid-zinc salt; 2-hydroxy-2-sulfinato propionatic acid-disodium salt; ethyl 2-hydroxy-2-sulfinato propionate-sodium salt.
- 5. The vinyl acetate polymer based emulsion of Claim 4 wherein the vinyl acetate-based emulsion polymer is formed using a redox catalytic system of hydrophobic hydroperoxide and the glycolic acid adduct of sodium sulfonate.
- 6. The vinyl acetate polymer based emulsion of Claim 3 wherein M is sodium or zinc.
- The vinyl acetate polymer based emulsion of Claim 3 wherein R₁ is OH.

N:\DOCNOS\06000-06099\06076\US\APPLN\06076USA.doc

ABSTRACT OF THE DISCLOSURE

The invention is the use of a glycolic acid adduct of sodium sulfite as the reducing agent in the redox couple for polymerization of vinyl acetate polymer based emulsions for nonwoven binders which contain formaldehyde, primarily from the self-crosslinking co-monomer N-methylolacrylamide.

10

N:\DOCNOS\06000-06099\06076\US\APPLN\06076USA.doc

DECLARATION FOR UTILITY OR DESIGN PATENT APPLICATION (37 CFR 1.63)

 □ Declaration Submitted with Initial Filing

OR

□ Declaration Submitted after Initial Filing (surcharge (37 CFR 1.16 (e)) required)

Attorney Docket Number	06076 USA			
First Named Inventor	Joel Erwin Goldstein			
COMPLETE IF KNOWN				
Application Number	/			
Filing Date				
Group Art Unit				
Examiner Name				

As a below named invento	or, I hereby declare that:							
My residence, post office address, and citizenship are as stated below next to my name.								
* - t 1 t 1 A A	irst and sole inventor (if only o the subject matter which is cla te Nonwoven Binders w	amed and for which a haten	i is suuuni on uit	and joint invento e invention entitle	r (if plural d:			
the specification of which is attached hereto	(Title	of the Invention)						
OR was filed on (MM/Di	DMYY)	as United	States Applicati	on Number or PC	T International			
Application Number		as amended on (MM/DD/YY			(if applicable).			
amended by any amendmen	viewed and understand the cont specifically referred to abovisclose information which is m	e.			ns, as			
		which designated at least	annlication for r	atent or inventor				
Prior Foreign Application Number(s)	Country	Foreign Filing Date (MM/DD/YYYY)	Priority Not Claimed	Certified Co YES	py Attached? NO			
Number(3)			0000	0000	0000			
	ation numbers are listed on a	supplemental priority data s	heet PTO/SB/02	B attached hereto):			
Additional foreign applica	under 35 U.S.C. 119(e) of any	United States provisional a	pplication(s) liste	ed below.				
Application Numbe		e (MM/DD/YYYY)		onal provision	al annlication			
			numb suppl	ers are listed of emental priority SB/02B attach	on a y data sheet			
1	1							

[Page 1 of 2]

Burden Hour Statement: This form is estimated to take 0.4 hours to complete. Time will vary depending upon the needs of the individual case. Any comments on the amount of time you are required to complete this form should be sent to the Chief Informa tion Officer, Patent and Trademark Office, Washington, DC 20231. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO. Assistant Commissioner for Patents, Washington, DC 20231.

	_	
Please type a plus sign (+) inside this box	-	LŁJ

s sign (+) inside this box

Approved for use through 9/30/00. OMB 0651-0032

Patent and Trademark Office; U.S. DEPARTMENT OF COMMERCE

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it contains a valid OMB control number. a valid OMB control number.

DECLARATION — Utility or Design Patent Application

I hereby claim the benefit to United States of America, United States or PCT Inter information which is mater and the national or PCT in	listed below and, national applicational to patentability	insorar a n in the m as define	as the subject is nanner provided ed in 37 CFR 1	Haller U	first paragraph of	135 11 5 6 1	12 Lackr	nowledg	eth eduty to	nating the the prior disclose pplication
	nt Application	or PC			Parent Filing Date Pa (MM/DD/YYYY)				t Patent Nu f applicable	
	Number				(MM/DU/	1111)			парриосы	7
		·····								
Additional U.S. or PC	T international an	olication r	numbers are list	ed on a	supplemental pri	ority data she	et PTO/S	SB/02B	attached h er	reto.
As a named inventor, I her	eby appoint the fo	lowing re	gistered practiti	oner(s)	to prosecute this	application a	nd to trar	isact al	I business in	
and Trademark Office con	nected therewith:	X Cus	stomer Nun		225 11151 CHIL 21222		→	·	Place Custon Number Bar C	
		☐ Re	distered pra			liste	d below	_L_	Label here	
Name			Regis Nu			ame	•		Registi Num	
Iyanio					23543					
			A	ir Produ	icts and Chemic	ais, inc.				ļ
11			-							'
Additional registered	practitioner(s) nan	ned on su	pplemental Reg	istered	Practitioner Infor	mation sheet	PTO/SB/	02C att	ached her et	o
Direct all corresponde		ıstomer				¬ OR			ndence addre	ess helow
Direct all conception		Bar Co				<u> </u>		Пооро		
				::::::::::::::::::::::::::::::::::::::						
Name				23	543				<u> </u>	
Address			Air Pro		nd Chemicals, In	ıc.				
Address										
City		,			State		ZIP			
Country			Telephone				Fax			
I hereby declare that all believed to be true; and punishable by fine or im application or any patent	further that these prisonment, or bo									elief are made are idity of the
Name of Sole or F	irst Inventor				A petitio	n has been	filed for	r this u	nsigned inve	ntor
Given Nar	ne (first and mid	idle [if a	iny])			Famil	y Name	or Su	name	
Joel Erwi	n				Golds	stein			,	
Inventor's Signature	Joel &	ini-	Mo.	YS	er _				Date	10/26/01
Residence: City	Allentown		1 1	PA	Country	USA			Citizenship	USA
Post Office Address	1127 N. 27	th Stre	et							
Post Office Address										
City	Allentown	State	PA	Z	IP .	18104	Cou	intry	USA	
	ors are being na	med on	the one sup	pleme	ntal Additional	Inventor(s)	sheet(s) PTO	/SB/02A atta	ched here

valid OMB control number.

DECLARATION

ADDITIONAL INVENTOR(S) Supplemental Sheet Page __1 of __1

Name of Additional Joint Inventor, if any:										
Given Na	me (first and middle [if any])		Family Name or Sumame						
Christian Le	onard				Dar	niels				
Inventor's Signature	Christ J. E	Jan	je Q	_			ž	26 0 <i>d</i> 20 Date	æ	
Residence: City	Macungie	State	PA	c	ountry	USA		Citizensh	ip U	SA
Post Office Address	7438 Catalpa Drive									
Post Office Address										
City	Macungie	State	PA		ZIP	18049	ountr	y USA		
Name of Addition	nal Joint Inventor, if a	ny:			A petitio	n has been filed	for t	his unsigi	ned in	ventor
Given Na	me (first and middle [if any	/])		\bot		Family Nam	e or	Sumame		
Chung-l	Ling					Мао				
Inventor's Signature	Ching &	Pm	lav	(0/26/0 Date						
Residence: City	Emmaus	State	PA	G	ountry	USA		Citizen	ship	USA
Post Office Address	4696 Sweetbriar C	ircle								
Post Office Address										
City	Emmaus	State	РА		ZIP	18049	Cou	ntry US	SA	
Name of Addition	nal Joint Inventor, if a	ny:			A petitio	n has been file	d for t	his unsig	ned in	ventor
Given Na	me (first and middle [if an	/])				Family Nan	ne or	Surname		
inventor's Signature								Da	te	
Residence: City		State			Country			Citizer	ıship	
Post Office Address										
Post Office Address					· ·					
City		State			ZIP			Country		

Burden Hour Statement: This form is estimated to take 0.4 hours to complete. Time will vary depending upon the needs of the individual case. Any comments on the amount of time you are required to complete this form should be sent to the Chief Information Officer, Patent and Trademark Office, Washington, DC 20231. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Assistant Commissioner for Patents, Washington, DC 20231.